



senotherm®
THE HIGH TEMPERATURE COATINGS

POWDER COATINGS

Base

Colours

Finish

Gloss

Recommended dry film thickness

Coverage m²/per kg

Pre-treatment

Curing

Temperature resistance

senotherm® CLASSIC POWDER 500

silicone

black, black metallic,
deep black

fine texture, smooth

matt

40 – 60 µm

10,4 – 15,6 m²

sandblasting

15 min./230°C

500°C

senotherm® CLASSIC POWDER 300

silicone

black, black metallic,
deep black

fine texture, smooth

matt

40 – 60 µm

10,4 – 15,6 m²

sandblasting

15 min./230°C

300°C

senotherm® CLASSIC POWDER 200

polyester

black, white,
(many colours available)

fine texture

semi-matt

60 – 80 µm

7,8 – 10,4 m²

degreasing

10 min./160°C

200°C